

CLASSIFICATION

EN ISO 16834 : G Mn3NiCrMo
AWS A5.28: ER100S-G

(*) Nearest classification

GENERAL DESCRIPTION

It is a low alloyed GMA welding wire, used for the welding fine-grained and high strength steels with a yield strength up to 680 N/mm². Especially used for low temperature applications that are manufactured from Ni-Cr-Mo steels.

Industry: Bridge, tank and railway fabrication, mining and ship building industry.

CHEMICAL COMPOSITION (W%) TYPICAL, WIRE

C	Si	Mn	Ni	Cr	Mo	Cu
0.09	0.75	1.60	0.60	0.55	0.25	< 0.25

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

Yield Strength	: 680 N/mm ²
Tensile Strength	: 770 N/mm ²
Elongation (L=5d)	: 24 %
Impact (ISO-V)	: 110 J (+20°C) 60 J (-40°C)

SHIELDING GASES (ISO 14175 / EN 439)

MAG : M21 - Ar + 5-25% Co₂
C1 - Co₂ (100%)

Current Type and Polarity : DC (+)

MATERIALS TO BE WELDED

	DIN	EN
Fine Grained Steels	StE 460 - StE 620	S620Q ; P460N
Heat Treated Fine Grained Structural Steels	N-A-XTRA 56, N-A-XTRA 63, N-A-XTRA 70 T1, T1A, T1B	S550QL1, S620QL1, S690QL1 -
Pipe Materials	X60, X65, X70, X80 (API 5LX) -	- L485MB, L555MB

PACKING AND DIAMETER INFORMATIONS

Diameter	0.8	1.0	1.2	1.6	2.0	2.4	3.2	Spool Weight
MIG/MAG Wire	X	X	X	-	-	-	-	15 kg

Liability : All information in this data sheet is based on the best available knowledge, is subject to change without notice and can only be considered as suitable for general guidance.

Fumes : Consult information on Welding Safety Sheet, available upon request.

Lion International U.K (M.E.) Limited

Monomark House, 27 Old Gloucester Street, London WC1N 3XX, United Kingdom.
T: +44 20 74198760 F: +44 20 78319489 E: info@lionintweld.co.uk

Lion International Middle East FZC

P.O. Box 41654, W/H No. 1K-01/4, Hamriyah Free Zone, Sharjah, UAE.
T: +971 6 5260461 F: +971 6 5260561 E: info.me@lionintweld.co.uk