

CLASSIFICATION

EN ISO 21952-A : G CrMo2Si*
AWS A5.28: ER90S-B3

(*) Nearest classification

GENERAL DESCRIPTION

It is a low alloyed GMA welding wire, used for the welding high temperature strength Cr-Mo (2.25 % Cr, 1.0 % Mo) steels (boiler and pressure vessels) in operating temperatures up to 600°C. It gives a weld metal that is resistant to corrosion and sulphide materials.

Industry: Oil industry, thermal plant, chemical and petro-chemical industry.

CHEMICAL COMPOSITION (W%) TYPICAL, WIRE

C	Si	Mn	Ni	Cr	Mo	Cu
0.08	0.50	0.60	< 0.20	2.40	1.00	< 0.30

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

Yield Strength	: 540 N/mm ²
Tensile Strength	: 640 N/mm ²
Elongation (L=5d)	: 22 %
Impact (ISO-V)	: 150 J (+20°C) 90 J (-10°C)

SHIELDING GASES (ISO 14175 / EN 439)

MAG : M21 - Ar + 5-25% Co₂
C1 - Co₂ (100%)

Current Type and Polarity : DC (+)

MATERIALS TO BE WELDED

	DIN	EN	Wr. Nr
Creep Resistant Steels	-	10CrMo9-10	1.7380
	10 CrSiMoV 7	-	1.8075
	10 CrV 63	-	-
	12 CrSiMo 8	-	-
Cast Steels	GS-25 CrMo 4	G25CrMo4	1.7218
	GS-17 CrMo 5 5	G17CrMo5-5	1.7357
	GS-18 CrMo 9 10	G17CrMo9-10	1.7379

PACKING AND DIAMETER INFORMATIONS

Diameter	0.8	1.0	1.2	1.6	2.0	2.4	3.2	Spool Weight
MIG/MAG Wire	-	X	X	-	-	-	-	15 kg

Liability : All information in this data sheet is based on the best available knowledge, is subject to change without notice and can only be considered as suitable for general guidance.

Fumes : Consult information on Welding Safety Sheet, available upon request.

Lion International U.K (M.E.) Limited

Monomark House, 27 Old Gloucester Street, London WC1N 3XX, United Kingdom.
T: +44 20 74198760 F: +44 20 78319489 E: info@lionintweld.co.uk

Lion International Middle East FZC

P.O. Box 41654, W/H No. 1K-01/4, Hamriyah Free Zone, Sharjah, UAE.
T: +971 6 5260461 F: +971 6 5260561 E: info.me@lionintweld.co.uk